

LAVA 20 & LAVA 20 CATALYST MIXING

- If you use the full catalyst (0.75 kg Catalyst with 25 kg Lava 20), you can apply a maximum of 3 mm or 118 mils thick coating in a single coat and it will cure within 3 to 5 hours.
- If no catalyst is used, you can apply a maximum of 1.5 mm or 59 US mils in one coat and it will dry over 7 to 10 hours.
- If not using catalyst, we recommend either a two coat application or incorporating matting in this scenario.



Lava 20 6 KG
(13.23 lbs / 1.59 US gal)
+
Lava 20 Catalyst 0.18 KG
(0.397 lbs / 0.0476 US gal)



Lava 20 15 KG
(33.07 lbs / 3.96 US gal)
+
Lava 20 Catalyst 0.45 KG
(0.99 lbs / 0.118 US gal)



Lava 20 25 KG
(55.12 lbs / 6.60 US gal)
+
Lava 20 Catalyst 0.75 KG
(1.65 lbs / 0.198 US gal)